## TRAFFIC PAINT

Formulated to match U.S.A., Egyptian specifications, and requirements II- P-115 D W.S.A. According to the Egyptian, standard No. 794/1995 and Federal specifications.

It is a ready mixed pigmented synthetic resin suitable for use on Portland cement, bitumen, pavement for runways, highways, streets, bridges, tunnels, etc., It is a fast drying traffic paint.

Advantages Good adhesion, waterproof, weathering resistance.

Technical	Colour match	White – yellow -black
Data	Pigment %by wt.	50-53
	No volatile % by Wt. of binder	31 min.
	Weight per lit.	$1.43 \pm 0.1$
	Drying (no Pick up) mins at 250 C	25max.
	Dry opacity-white not less than	0.86
	Yellow not less than	0.90
	Uncombined water not over	1 % by wt.
	Particles retained on 325 sieve	·
	not over	1 % by wt.
	Consistency	70-80 Kw.
	Grind	not under 3 micron
	Directional reflectance	not less than 6 months
	Thinner	Euxit 501 or universal
		Thinner.
	Shelf life (month)at 250 C	12
	Thinner	Up to 15 % by volume
	Spreading rate for DFT 100 mic.	5m2/kg
	Sold by volume	50%

-30-

Package

20

200

Kgs